

IN THE CLAIMS

Please cancel claims 1 - 16 and 32 - 51 without prejudice.

1. Cancelled
2. Cancelled
3. Cancelled
4. Cancelled
5. Cancelled
6. Cancelled
7. Cancelled
8. Cancelled
9. Cancelled
10. Cancelled
11. Cancelled
12. Cancelled
13. Cancelled
14. Cancelled
15. Cancelled
16. Cancelled
17. (Original) A process of making a sorbent composition,  
said process comprising the steps of:

- (a) admixing zinc oxide and a carrier to provide a support mix;
- (b) particulating the support mix to provide a support particulate;
- (c) incorporating said support particulate with a noble metal to provide a promoted particulate comprising an unreduced noble metal; and
- (d) reducing said promoted particulate to provide a reduced sorbent composition comprising a reduced-valence noble metal.

18. (Original) A process in accordance with claim 17 wherein said reduced-valence noble metal has a valence which is less than the valence of said unreduced noble metal.

19. (Original) A process in accordance with claim 18 wherein said carrier comprises a silica compound and an alumina compound.

20. (Original) A process in accordance with claim 17 wherein said reduced-valence noble metal has a valence of less than 2.

21. (Original) A process in accordance with claim 20 wherein said promoted particulate is dried and calcined before reduction.

22. (Original) A process in accordance with claim 21 wherein said support particulate is dried and calcined before incorporation with said noble metal.

23. (Original) A process in accordance with claim 22 wherein said reduced-valence noble metal comprises platinum.

24. (Original) A process in accordance with claim 17 wherein said support mix is selected from the group consisting of a wet mix, a dough, a paste, and a slurry, and wherein said support particulate is selected from the group consisting of a granulate, an extrudate, a tablet, a sphere, a pellet, and a microsphere.

25. (Original) A process in accordance with claim 24 wherein said support particulate comprises a microsphere.

26. (Original) A process in accordance with claim 17 wherein said support mix is in the form of a slurry and said particulating comprises spray drying said slurry to form a microsphere.

27. (Original) A process in accordance with claim 26 wherein said microsphere has a mean particle size in the range of from about 1 micrometer to about 500 micrometers.

28. (Original) A process in accordance with claim 17 wherein said incorporating is selected from the group consisting of impregnating, soaking, spraying, and combinations thereof.

Art Unit: \*\*\*

CLMPTO

June 24, 2004

29. (Original) A process in accordance with claim 17 wherein said incorporating comprises incipient wetness impregnation.

30. (Original) A process in accordance with claim 17 wherein said reduced-valence noble metal has a valence of zero.

31. (Original) A process in accordance with claim 30 wherein said reduced-valence noble metal component comprises platinum.

Claims 32-51 are canceled.